

Classifications

EN ISO 14343-A

W 25 4

Characteristics and typical fields of application

GTAW rod for gas-shielded welding of heat resisting, analogous or similar steels. Ferritic-austenitic deposit. The low Ni-content renders this filler metal especially recommendable for applications involving the attack of sulphurous oxidizing or reducing combustion gases. Scaling resistance up to + 1100°C.

Base materials

Ferritic-austenitic

1.4821 X15CrNiSi25-4, 1.4823 GX40CrNiSi27-4

Ferritic-perlitic

1.4713 X10CrAlSi7, 1.4724 X10CrAlSi13, 1.4742 X10CrAlSi18, 1.4762 X10CrAlSi25, 1.4710 GX30CrSi7, 1.4740 GX40CrSi17

AISI 327, ASTM A297HC

Typical analysis the TIG rods (wt.-%)


	C	Si	Mn	Cr	Ni
wt-%	0.07	0.8	1.2	25.7	4.5

Mechanical properties of all-weld metal

Condition	Yield strength R _e	Tensile strength R _m	Elongation A (L ₀ =5d ₀)	Impact work ISO-V KV J
	MPa	MPa	%	+20 °C
u	540 (≥ 450)	710 (≥ 650)	22 (≥ 15)	70

u untreated, as welded – shielding gas Argon

Operating data

	Polarity: DC (-)	Shielding gas: 100 % Argon	Rod marking: front: ✦ W 25 4 back: 1.4820	ø (mm) 2.4
-------------------------------------------------------------------------------------	------------------------------	--------------------------------------	--------------------------------------------------------	----------------------

Preheating and interpass temperature as required by the base metal.