

Classifications

| EN ISO 17632-A | EN ISO 17632-B | AWS A5.36 | AWS A5.36M |
|----------------|----------------|--------------------|---------------------|
| T46 4 B M 3 H5 | T556T5-0MA-H5 | E70T5-M21A4-CS1-H4 | E490T5-M21A4-CS1-H4 |
| T42 4 B C 3 H5 | T496T5-0CA-H5 | E70T5-C1A4-CS1-H4 | E490T5-C1A4-CS1-H4 |

Characteristics and typical fields of application

Seamless basic flux cored wire for single- or multilayer welding of Carbon, Carbon-Manganese steels and similar steels, including fine grain steels with Argon-CO₂ shielding gas or pure CO₂. Main features: excellent weldability in flat and horizontal position, smooth and bright bead, very low spatter losses, easy to remove slag and exceptional mechanical properties even at low temperatures. This wire is especially suitable for welding components of different material or as buffer layer for hardfacing applications.

Base materials

S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P275NL1-P460NL1, P215NL, P265NL, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE240

Ship building steels: A, B, D, E, A 32-E 36

ASTM A 106 Gr. A, B, C; A 181 Gr. 60, 70; A 283 Gr. A, C; A 285 Gr. A, B, C; A 350 Gr. LF1; A 414 Gr. A, B, C, D, E, F, G; A 501 Gr. B; A 513 Gr. 1018; A 516 Gr. 55, 60, 65, 70; A 573 Gr. 58, 65, 70; A 588 Gr. A, B; A 633 Gr. C, E; A 662 Gr. B; A 711 Gr. 1013; A 841 Gr. A; API 5 L Gr. B, X42, X52, X56, X60, X65

Typical analysis of all-weld metal (wt.-%)

| | Gas | C | Si | Mn |
|------|-----|------|------|-----|
| wt-% | M21 | 0.07 | 0.55 | 1.6 |
| wt-% | C1 | 0.06 | 0.50 | 1.3 |


Mechanical properties of all-weld metal

| Condition | Yield strength R _e | Tensile strength R _m | Elongation A (L ₀ =5d ₀) | Impact work ISO-V KV J | | |
|-----------|----------------------------------|------------------------------------|--|---------------------------|------------------|-----------|
| | MPa | MPa | % | +20 °C | -40°C | -60°C |
| u | 500 (≥460) | 610 (550–660) | 28 (≥20) | 160 (≥47) | 100 (≥47) | 80 |
| u1 | 430 (≥420) | 510 (500–640) | 29 (≥20) | 140 | 80 (≥47) | |

u untreated, as welded – shielding gas M21

u1 untreated, as welded – shielding gas C1

Operating data

|  | Polarity: DC (+) | Shielding gases: (EN ISO 14175) M21 – M35; C1 | ø (mm) |
|---|----------------------------|--|--------|
| | | | 1.0 |
| | | | 1.2 |
| | | | 1.4 |
| | | | 1.6 |

Welding with standard GMAW-facilities possible

Approvals

TÜV(12575), DB(42.014.46), GL(4YH5S/M21+C1), DNV(4YMS(H5)/M21+C1), ABS(4YSAH5/M21+C1), LR, BV(SA4YM/M21+C1), RINA(4YSH5/M21+C1), CE