

Classifications

EN ISO 14172	AWS A5.11	Mat. No.
E Ni 6182 (NiCr15Fe6Mn)	ENiCrFe-3	2.4620

Characteristics and typical fields of application

Nichtrostend, zunderbeständig bis 950 °C, hochwarmfest bis 800 °C, kaltzäh bis –196 °C. Gut geeignet für Austenit-Ferrit-Verbindungen; auch bei Wärmebehandlungen über 300 °C keine verspröden Cr-Karbidzonen im Übergang Ferrit / Schweißgut. Gut für zähe Verbindungen und Auftragungen an hitzebeständigen Cr- und CrNi-Stählen/Stahlgussorten und

Ni-Basislegierungen. Temperaturbegrenzungen: 500 °C in S-haltigen Atmosphären, max. 800 °C für vollbelastete Nähte. Für Schweißungen an kaltzähnen Stählen/Stahlgussorten einschließlich der vergütbaren Ni-Stähle. Für Verbindungen an Stählen mit niedrigen Ausdehnungskoeffizienten (Dilavar, Inval).

Base materials

TÜV-eignungsgeprüfte Grundwerkstoffe

1.4876 – X10NiCrAlTi32-20; 2.4816 – NiCr15Fe;

Kaltzähe 1.5 – 5 %ige Ni-Stähle; X8Ni9.

Mischverbindungen zwischen 1.4583 – X10CrNiMoNb18-12 und ferritischen Kesselstählen bis 16Mo3; Alloy 800 (H)

Typical analysis of all-weld metal (wt.-%)

	C	Si	Mn	Cr	Ni	Nb	Fe
wt-%	< 0.05	< 0.5	6.5	16	Bal.	2.0	< 6.0

Structure: Austenite

Mechanical properties of all-weld metal

Heat-treatment	Yield strength $R_{p0.2}$	Yield strength $R_{p1.0}$	Tensile strength R_m	Elongation A ($L_0=5d_0$)	Impact work ISO-V KV J	
	MPa	MPa	MPa	%	+20 °C	-196 °C
aw	350	380	620	35	90	70

Creep rupture properties: According to matching/similar high temperature resistant metals up to 800 °C (1472 °F).

Operating data

Polarity: DC (+)	Ø (mm)	L mm	Amps A
↑ ↓	2.5	300	45 – 70
↑ ↓	3.2	300	65 – 100
↑ ↓	4.0	350	95 – 130
↑ ↓	5.0	400	130 – 160

Welding instruction

Materials	Preheating	Postweld heat treatment
Unalloyed/low alloy steels to austenitic CrNi(Mo,N) steels / cast steel grades	Ferritic side, according to parent metal	According to parent metal. Attention must be paid to intercrystalline corrosion and embrittlement in the case of stainless austenitic steels / cast steel grades
Stainless/heat resistant Cr steels / cast steel grades to austenitic CrNi(Mo,N) steels / cast steel grades	According to parent metal	According to parent metal
Cryogenic Ni steels	According to parent metal	According to parent metal

Approvals

TÜV (02073), TÜV (KTA) (08128.00), CE